

**NSBO-10 TDS**

Property	Test Method	Value	Unit
Transmittance	ASTM E 424 1971 6. 5. 2	<0.2	%
Tensile Strength (warp/weft)	ISO 13934-1:1999 C.R.E.STRIP METHOD	532.3 452.5	N/5cm
Tearing Strength (warp/weft)	ISO 13937-2:2000 C.R.E. SINGLE TONGUE METHOD	8.5 4.4	N
Elongation (warp/weft)	ISO 13934-1:1999 C.R.E.STRIP METHOD	47.8 33.6	%
Adhesion Strength (warp/weft)	ISO 2411:1991 C.R.E	59 59	N/5cm
Flexing Endurance	DIN 53351, FLEXOMETER METHOD	10	CYCLES
Resistance to Low Temp. (warp/weft)	ISO 13934-1:1999 -20 , 5HRS	94.4 99.4	%
Resistance to High Temp. (warp/weft)	ISO 13934-1:1999 80 , 5HRS	97.3 100.2	%
Colorfastness to Weathering	ASTM G 26, METHOD A, TYPE B	3.5	grade
Weight		250	g/m <sup>2</sup>

For more information, visit our website at  
[www.star-flex.com](http://www.star-flex.com)